

Technical Data Sheet

ARMA CPV

Description	ARMA CPV is a polyester reinforced elastomeric modified bitumen membrane, self-protected with a mineral surface. The selvedge is 7cm wide.
Use	Cap sheet for details.
Application method	Fully bonded, with fully sealed joints, using torch-on technique to form continuous layer.
Storage	Rolls to be stored upright and away from heat.
Composition	(indicative)

Reinforcement (g/m²) :	Stabilised polyester	120
Binder (g/m²) :	Elastomer	4,000
Surface finish (g/m²) :	Mineral slates	1,000
Under surface finish (g/m²) :	Thermofusible film	10

Characteristics		Standards (BS)	Units	Value	Tolerance		
					Min	Max	
Dimensions	Length	EN 1848-1	m	5	-1%		
	Width		m	1	-1%		
	Straightness		-	Pass			
	Nominal roll weight	EN 1849-1	kg	28			
	Thickness (selvedge)		mm	3.65			
Visible defects	New product	EN 1850-1	-	None			
	After ageing to EN 1297		-	NA			
Adhesion of granules		EN 12039	%	15	0	30	
Resistance to tearing (nail shank)	Longitudinal	EN 12310-1	N	NA	-	-	
	Cross direction			NA	-	-	
Tensile properties: maximum tensile force	Longitudinal	EN 12311-1	N/50 mm	450	320	550	
	Cross direction			270	250	300	
Tensile properties: elongation	Longitudinal	EN 12311-1	%	25	10	50	
	Cross direction			25	10	50	
Peel resistance of joint	Maximum force	EN 12316-1	N/50mm	Selvedge	NA	-	-
				End joint	NA	-	-
	Average force			Selvedge	NA	-	-
				End joint	NA	-	-
Shear resistance of joint	Maximum force	EN 12317-1	N/50mm	Selvedge	NA	-	-
				End joint	NA	-	-
Flexibility at low temperature	Surface	EN 1109	°C	-10	≤		
	Under surface			-10	≤		
Flow resistance at elevated temperature	New product	EN 1110	°C	90	≥		
	After ageing to EN 1296			90	85	110	
Resistance to impact		EN 12691	mm	NA	≤		
Resistance to static loading		EN 12730 (A)	kg	NA	≥		
Dimensional stability		EN 1107-1	%	0.3	≤		

Characteristics		Standards (BS)	Units	Value	Tolerance	
					Min	Max
Form stability under cyclic temperature change		EN 1108	%	NA		
Water vapour transmission properties	New product	EN 1931	-	μ=20000		
	After ageing to EN 1296		-	NA		
Watertightness	New product	EN 1928	-	Pass	at 10 kPa	
	After ageing to EN 1296		-	NA		
Watertightness after stretching at low temperature		EN 13897	%	NA		
Reaction to fire		EN 13501-1	-	PND		
Resistance to root penetration		EN 13948	-	NA		
Dangerous substances consult : http://europa.eu.int/comm/enterprise/construction/internal/dangsub/dangmain.htm		-	-	None		

NA=not applicable due to use of product. PND=Performance not determined.

The manufacturer reserves the right to modify, at any time, the characteristics of this product.