

Technical Data Sheet

HYRANGER 25/25 RE Base and Underlayer

1. Description	Hyranger 25/25 RE is a glass-fibre reinforced SBS elastomeric modified bitumen waterproofing membrane, sanded on both surfaces.
2. Use	Can be used as air and vapour control layer, base layer or underlayer in multi-layer waterproofing system for flat roofs.
3. Application method	Fully bonded, with fully sealed joints, by torch-on or pour and roll technique, to form a continuous layer.
4. Storage	Rolls to be stored upright and away from heat.
5. Composition	(Indicative).

Reinforcement (g/m²)	Glass-fibre	50
Binder (g/m²)	SBS elastomer	2,900
Surface finish (g/m²)	Sand	300
Under surface finish (g/m²)	Sand	300

Characteristics		Standards (BS)	Units	Value	Tolerance		
					Min	Max	
Dimensions	Length	EN 1848-1	m	7	-1%		
	Width		m	1	-1%		
	Straightness		-	Pass			
	Nominal roll weight		kg	25.4			
	Thickness (selvedge)	EN 1849-1	mm	2.65	2.50	2.80	
Visible defects	New product	EN 1850-1	-	None			
	After ageing to EN 1297		-	NA			
Adhesion of granules		EN 12039	%	NA	-	-	
Resistance to tearing (nail shank)	Longitudinal	EN 12310-1	N	80	50	150	
	Cross direction			80	50	150	
Tensile properties: maximum tensile force	Longitudinal	EN 12311-1	N/50mm	250	200	550	
	Cross direction			150	120	350	
Tensile properties: elongation	Longitudinal	EN 12311-1	%	3	2	4	
	Cross direction			3	2	4	
Peel resistance of joint	Maximum force	EN 12316-1	N/50mm	Selvedge	NA	-	-
				End joint	NA	-	-
	Average force			Selvedge	NA	-	-
				End joint	NA	-	-
Shear resistance of joint	Maximum force	EN 12317-1	N/50mm	Selvedge	NA	-	-
				End joint	NA	-	-
Flexibility at low temperature	Surface	EN 1109	°C	-16	≤		
	Under surface			-16	≤		
Flow resistance at elevated temperature	New product	EN 1110	°C	100	≥		
	After ageing to EN 1296			NA			
Resistance to impact		EN 12691	mm	500	≤		
Resistance to static loading		EN 12730 (A)	kg	PND	≥		
Dimensional stability		EN 1107-1	%	0.1	≤		
Form stability under cyclic temperature change		EN 1108	%	NA			

Characteristics		Standards (BS)	Units	Value	Tolerance	
					Min	Max
Water vapour transmission properties	New product	EN 1931	-	280		
	After ageing to EN 1296		-	280		
Watertightness	New product	EN 1928	-	Pass	<10 kPa	
	After ageing to EN 1296		-	Pass		
Watertightness after stretching at low temperature		EN 13897	%	NA		
Reaction to fire		EN 13501-1	-	PND		
Resistance to root penetration		EN 13948	-	NA		
Dangerous substances consult: http://europa.eu.int/comm/enterprise/construction/internal/dangsub/dangmain.htm		-	-	None		

NA=Not applicable due to use of product.

PND=Performance not determined.

Axter Ltd reserves the right to modify and update this data at any time without prior notice. Only the latest version of this document is valid, available for download at www.axter.co.uk/downloads. Once downloaded, documents are uncontrolled. Users should always confirm they are referring to the latest version prior to use. Further assistance is available from Axter Ltd's Technical Support Team, email: technical@axterltd.co.uk, telephone: 01473 935008.

The intended use of this product should be verified with Axter Ltd prior to adoption to ensure its suitability and compliance with specifications, project requirements, industry regulations, legislation, good practice, installation techniques and all other relevant guidance. Axter Ltd accepts no liability for non-compliant use of this product.