

Product Data Sheet

ADH-S ADHESIVE

ADH-S Adhesive is a specialist high-tack adhesive providing a safe and high performing method of bonding fleece-backed PVC (Ecoflex ADH) and bitumen (Force ADH) membranes to HYTHERM ADH PIR insulation boards.

ADH-S Adhesive securely bonds fleece-backed waterproofing membranes to PIR insulation board, due to its high tack and excellent adhesion. It creates a strong and lasting bond between the two, preventing the membrane from lifting and simplifying the installation process.

Key features

- Excellent coverage rate making it economical to use.
- High performance, heat resistant and durable.
- Non-flammable: eliminates 'hot works', safe to store on site.
- Securely bonds fleece-backed PVC and bitumen membranes to a range of tissue-faced insulation boards.
- Reduced need for intrusive mechanical fixings.
- Speedy installation time.

Packaging

ADH adhesive is supplied in a 20 litre (23kg) polybottle with handle for easy handling and pouring.

Application method

- Substrates suitable for*: Concrete, Timber, Metal Decks, Tissue & Foil-Faced PIR, RBM & BUR, Asphalt, Mineral Wool.
- Membranes suitable for*: Fleece-Backed PVC, TPO/TPE & EPDM.
- Ensure all surfaces are free from dust, grease and other contaminants.
- Apply ADH-S adhesive directly to the insulation board with a lambswool roller (it is a single-component, one-way stick moisture curing polyurethane (MCPU) adhesive).
- Leave the insulation board for a minimum of 5 minutes in order to allow the solvent to escape from the adhesive film.
- Roll the fleece-backed membrane into the ADH-S Adhesive and consolidate substrates using a 20kg water filled roller to prevent air entrapment.
- It cures rapidly in temperatures 5-30°C.
- Average coverage rate: Up to 100m² / 20 litres (23kg)*.

*Adhesion tests should be carried out prior to use. Applications only for substrates and membranes listed. All other substrates and membranes should be tested prior to use. Please contact Axter Ltd for more information.

TECHNICAL DATA	
Product	ADH-S Adhesive
Appearance	Pink
Application temperature	5 – 30°C
Temperature resistance	-30 – 140°C
Cure time (20°C)	90 minutes
Coverage*	Up to 100m ² / 20 litres (23kg)
Flash point	See MSDS
Viscosity	Roller-Applied
Storage temperature	5 - 25°C
Open time (20°C)	30 minutes
Shelf life	12 months

*Please note: Above information is provided as a guideline. Coverage rate stated is approximate, the porosity and type of supports/materials/ surface atmospheric conditions will affect coverage rates and potentially fall outside of the guideline given within the TDS. It is necessary for a test to be conducted prior to application to establish accurate coverage rates, cure times and other factors on a project specific bases to ensure suitability for the wide variety of requirements and condition on site.

Axter Ltd makes no warranties, express or implied, as to the properties and performance under any variations from such conditions in actual construction.

ADH-S Adhesive significantly exceeds requirements for wind uplift, as part of a full system build, as given in BS EN 1991-1-4 (which provides guidance for the structural design of buildings for wind). Further information is available from Axter Ltd.

Packaging

ADH-S Adhesive is a moisture-sensitive adhesive which will gel if left in open contact with air for any length of time. This product has been protected with a layer of nitrogen ensuring a shelf life of 12 months in a sealed and dry container stored at a temperature of 5 - 25°C. Once the container is opened, the layer of nitrogen will disappear and the adhesive will have a limited life.

It should be noted that carbon dioxide will be given off if water enters the adhesive container, which can cause pressurisation.

The hazard labels and Material Safety Data Sheet (MSDS) for this product must be read prior to use. Please contact Axter Ltd for further information.

Axter Ltd reserves the right to modify and update this data at any time without prior notice. Only the latest version of this document is valid, available for download at www.axter.co.uk/downloads. Once downloaded, documents are uncontrolled. Users should always confirm they are referring to the latest version prior to use. Further assistance is available from Axter Ltd's Technical Support Team, email: technical@axterltd.co.uk, telephone: 01473 935008.

The intended use of this product should be verified with Axter Ltd prior to adoption to ensure its suitability and compliance with specifications, project requirements, industry regulations, legislation, good practice, installation techniques and all other relevant guidance. Axter Ltd accepts no liability for non-compliant use of this product.