

Technical Data Sheet

FORCE LINE 4.5

1. Description	Force Line 4.5 is a polyester reinforced elastomeric (SBS) modified bitumen membrane. Its surface is finished with coloured mineral chippings. The minimum selvedge width is 6cm.
2. Use	Capsheet in a single or multi-layer roof waterproofing system.
3. Application Method	Fully bonded, with fully sealed joints, using torch-on technique to form continuous layer.
4. Storage	Rolls to be stored upright and away from heat.
5. Composition	(Indicative). See below.

Reinforcement (g/m²) :	Stabilised polyester	180
Binder (g/m²) :	SBS elastomer	3,900
Surface finish (g/m²) :	Mineral slates	1000
Under surface finish (g/m²) :	Thermofusible film	10

Characteristics		Standards (BS)	Units	Value	Tolerance		
					Min	Max	
Dimensions	Length	EN 1848-1	m	8	-1%		
	Width		m	1	-1%		
	Straightness		-	Pass			
	Nominal roll weight	EN 1849-1	kg	44			
	Thickness (on finished product)		mm	4.1	3.9	4.3	
Visible defects	New product	EN 1850-1	-	None			
	After ageing to EN 1297		-	NA			
Adhesion of granules		EN 12039	%	15	-	-	
Resistance to tearing (nail shank)	Longitudinal	EN 12310-1	N	NA	-	-	
	Cross direction			NA	-	-	
Tensile properties: maximum tensile force	Longitudinal	EN 12311-1	N/50mm	700	400	850	
	Cross direction			550	400	700	
Tensile properties: elongation	Longitudinal	EN 12311-1	%	40	30	50	
	Cross direction			50	40	60	
Peel resistance of joint	Maximum force	EN 12316-1	N/50mm	Selvage	NA	-	-
				End joint	NA	-	-
	Average force			Selvage	NA	-	-
				End joint	NA	-	-
Shear resistance of joint	Maximum force	EN 12317-1	N/50mm	Selvage	550	400	700
				End joint	700	400	850
Flexibility at low temperature	Surface	EN 1109	°C	-10	≤		
	Under surface			-10	≤		
Flow resistance at elevated temperature	New product	EN 1110	°C	100	≥		
	After ageing to EN 1296			100	90	110	
Resistance to impact		EN 12691	mm	600	≤		
Resistance to static loading		EN 12730 (A)	kg	20	≥		
Dimensional stability		EN 1107-1	%	0.3	≤		
Form stability under cyclic temperature change		EN 1108	%	NA			

Water vapour transmission properties	New product	EN 1931	-	$\mu=20000$	
	After ageing to EN 1296		-	NA	
Watertightness	New product	EN 1928	-	Pass	<10kPa
	After ageing to EN 1296		-	NA	
Watertightness after stretching at low temperature		EN 13897	%	NA	
Reaction to fire		EN 13501-1	-	NPD	
Resistance to root penetration		EN 13948	-	NA	

NA=not applicable due to use of product.

NPD=No performance determined.

The manufacturer reserves the right to modify, at any time, the characteristics of this product.

Axter Ltd reserves the right to modify and update this data at any time without prior notice. Only the latest version of this document is valid, available for download at www.axter.co.uk/downloads. Once downloaded, documents are uncontrolled. Users should always confirm they are referring to the latest version prior to use. Further assistance is available from Axter Ltd's Technical Support Team, email: technical@axterltd.co.uk, telephone: 01473 935008.

The intended use of this product should be verified with Axter Ltd prior to adoption to ensure its suitability and compliance with specifications, project requirements, industry regulations, legislation, good practice, installation techniques and all other relevant guidance. Axter Ltd accepts no liability for non-compliant use of this product.